



441 DeGroate Rd., New Lenox, IL 60451
 815-462-0939 Fax: 815-485-1194
www.dpswax.com
 email: info@dpswax.com

DPS/MORRIS WAX
 A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111
 913-948-6220 Fax: 913-948-6242
www.sacopetroleum.com



500 N. National, Springfield, MO 65804
 417-869-7333 Fax: 417-831-4671
www.morriswax.com
 email: ghudson@morriswax.com

1260 Paraffin Wax

1260 is a fully refined paraffin wax used for tapers, pillars, and molds.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Congealing Point °F (°C)	D938	154 (67.8)	166 (74.4)	157 (69.4)
Kinematic Viscosity, cSt @210°F (98.9°C)	D445	5.7	7.9	7.5
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	44.9	52.1	50.8
Oil Content, Wt%	D721	----	1.0	----
Saybolt Color	D6045	+25	----	+28
Odor	D1833	----	1	0
Needle Penetration, dmm @ 77°F (25°C)	D1321	----	18	12
Specific Gravity @77°F (25°C)		----	----	0.927

SHIPPED:

10 lb. slabs in 62 lb. cartons or 2000 lb. covered gaylords

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710, 21 CFR 176.170 and 21 CFR 176.18 for use in contact with food and in 21 CFR 172.886 or use in food.