



441 DeGroate Rd., New Lenox, IL 60451
815-462-0939 Fax: 815-485-1194
www.dpswax.com
email: info@dpswax.com

DPS/MORRIS WAX
A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111
913-948-6220 Fax: 913-948-6242
www.sacopetroleum.com



500 N. National, Springfield, MO 65804
417-869-7333 Fax: 417-831-4671
www.morriswax.com
email: ghudson@morriswax.com

Parafflex® 4633A (Astorlite® J223)

PARAFFLEX® 4633A is our newest jar candle formulation designed specifically to enhance both hot and cold fragrance throw. The wax performs best when poured at 145 - 155°F into a heated container.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D 127	124 (51.1)	132 (55.6)	128 (53.3)
Congealing Point °F (°C)	D 938	120 (48.9)	128 (53.3)	124 (51.1)
Saybolt Color	D 6045	+8	----	----
Needle Penetration, dmm @ 77°F (25°C)	D 1321	96	120	108

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.