



441 DeGroate Rd., New Lenox, IL 60451
815-462-0939 Fax: 815-485-1194
www.dpswax.com
email: info@dpswax.com

DPS/MORRIS WAX
A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111
913-948-6220 Fax: 913-948-6242
www.sacopetroleum.com



500 N. National, Springfield, MO 65804
417-869-7333 Fax: 417-831-4671
www.morriswax.com
email: ghudson@morriswax.com

Parafflex® 4636A (Astorlite® J50)

PARAFFLEX® 4636A is a soft white, opaque wax specially designed for jar / container candles. Its cohesive strength and low shrinkage allow it to adhere to the container. Jar / container candles can be made with a single filling with no top-off necessary.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D 127	128 (53.3)	136 (57.8)	132 (55.6)
Congealing Point °F (°C)	D 938	124 (51.1)	132 (55.6)	128 (53.3)
Saybolt Color	D 6045	+8	----	----
Needle Penetration, dmm @ 77°F (25°C)	D 1321	86	110	98

FDA STATUS:

Please contact an IGI representative for information concerning the FDA status of this product.