



441 DeGroate Rd., New Lenox, IL 60451  
 815-462-0939 Fax: 815-485-1194  
[www.dpswax.com](http://www.dpswax.com)  
 email: [info@dpswax.com](mailto:info@dpswax.com)

DPS/MORRIS WAX  
 A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111  
 913-948-6220 Fax: 913-948-6242  
[www.sacopetroleum.com](http://www.sacopetroleum.com)



500 N. National, Springfield, MO 65804  
 417-869-7333 Fax: 417-831-4671  
[www.morriswax.com](http://www.morriswax.com)  
 email: [ghudson@morriswax.com](mailto:ghudson@morriswax.com)

## 5702 -Micro Wax

**Micro Wax** is a white, laminating grade microcrystalline wax.

- Helps give a smooth appearance
- Eliminates wet spots
- Holds scent better
- Add 5% to 7%

### PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D127	170 (76.7)	180 (82.2)	175 (79.4)
Congeaing Point °F (°C)	D938	---	---	165 (73.9)
Kinematic Viscosity, cSt @ 210°F (98.9°C)	D445	14.3	18.0	16.0
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	75.0	90.0	82.0
Flash Point (C.O.C.), °F (°C)	D92	530 (277)	---	---
Saybolt Color	D156	+16	---	---
Odor	D1833	---	---	0.0
Needle Penetration, dmm @ 77°F (25°C)	D1321	25	35	30

### FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.