



SACO, DPS/MORRIS WAX

A Division of KWS Holdings LLC



441 DeGroate Rd., New Lenox, IL 60451  
815-462-0939 Fax: 815-485-1194  
[www.dpswax.com](http://www.dpswax.com) email: [info@dpswax.com](mailto:info@dpswax.com)

1601 Fairfax Traffic Way, Kansas City, KS 66115

500 N. National, Springfield, MO 65802  
417-869-7333 Fax: 417-831-4671  
[www.morriswax.com](http://www.morriswax.com)

## 5702 -Micro Wax

**Micro Wax** is a white, laminating grade microcrystalline wax.

- Helps give a smooth appearance
- Eliminates wet spots
- Holds scent better
- Add 5% to 7%

### PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D127	165 (73.9)	182 (83.3)	175 (79.4)
Congealing Point °F (°C)	D938	160 (71.1)	170 (76.7)	165 (73.9)
Kinematic Viscosity, cSt @ 210°F (98.9°C)	D445	13.8	18.0	16.0
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	75.0	90.0	82.0
Flash Point (C.O.C.), °F (°C)	D92	530 (277)	---	---
Saybolt Color	D156	+16	---	---
Odor	D1833	---	1.0	0.0
Needle Penetration, dmm @ 77°F (25°C)	D1321	20	35	30

### FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.