



815-462-0939

www.dpswax.com email: info@dpswax.com

DPS WAX, INC.

1601 Fairfax Traffic Way, North Entrance Kansas City, KS 66115

1260 Paraffin Wax

1260 is a fully refined paraffin wax used for tapers, pillars, and molds.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Congealing Point °F (°C)	D938	152 (66.7)	166 (74.4)	157 (69.4)
Kinematic Viscosity, cSt @210°F (98.9°C)	D445	5.7	7.9	7.5
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	44.9	52.1	50.8
Oil Content, Wt%	D721	----	1.0	0.47
Saybolt Color	D6045	+25	----	+28
Odor	D1833	----	1	0
Needle Penetration, dmm @ 77°F (25°C)	D1321	----	18	12
Specific Gravity @77°F (25°C)		----	----	0.927

SHIPPED:

10 lb. slabs in 60 lb. cartons or 2000 lb. covered gaylords

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710, 21 CFR 176.170 and 21 CFR 176.18 for use in contact with food and in 21 CFR 172.886 or use in food.