



DPS WAX, INC.

815-462-0939

www.dpswax.com email: info@dpswax.com

1601 Fairfax Traffic Way, North Entrance Kansas City, KS 66115

Parafflex® 4633A (Astorlite® J223)

PARAFFLEX® 4633A is our newest jar candle formulation designed specifically to enhance both hot and cold fragrance throw. The wax performs best when poured at 145 - 155°F into a heated container.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Drop Melt Point °F (°C)	D 127	124 (51.1)	132 (55.6)	128 (53.3)
Congealing Point °F (°C)	D 938	120 (48.9)	128 (53.3)	124 (51.1)
Saybolt Color	D 6045	+8	30	----
Kinematic Visc. @212°F (100°C)	D 445	5.0	7.5	
Odour	D 1833	0	1.0	0.5
Needle Penetration, dmm @ 77°F (25°C)	D 1321	95	126	108

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.